| Gerflor theflooringgroup | MURAL ULTRA DESIGN | | |
|---|---|---|---|
| **DESCRIPTION** | | | |
| Total thickness | - | mm | 1.50 |
| Thickness of transparent decorative layer | - | mm | 0.10 |
| Thickness of resistance layer | - | mm | 1.4 |
| Weight | - | g/sqm | 2450 |
| Width | EN 233 | cm | 200 |
| Length | EN 233 | lm | 21 |
| **CLASSIFICATION** | | | |
| Norm / Product specification | - | - | EN 259-1 |
| Fire classification | EN 13 501-1 | class | B- s2,d0 |
| **PERFORMANCES** | | | |
| Curving after exposure to heat | ISO 23999 - EN 434 | | ≤ 2 mm |
| Colour fastness | EN ISO 20 105 - B02 | degree | ≥ 6 |
| Surface treatment | - | - | PROTECSOL |
| Chemical resistance (1) | EN ISO 26987 | - | OK |
| Cleanability | EN 233 | | Washable and brushable |
| Emission of particles | ISO 14644-1 | class | Class 3 |
| Anti-bacterial activity (E. coli -S. aureus -MRSA (2) | ISO 22196 | - | > 99 % inhibits growth |
| Resistance to impacts | EN 259-2 | - | No visible bursting or cracking |
| Scratch resistance | NF EN 14565 annex A | | No visible deterioration |
| Determination of flexibility | EN ISO 24344 | | No damage, no cracking |
| Resistance of welded joints | EN 684 | N/50mm | ≥ 250 |
| **ENVIRONMENT / AIR QUALITY** | | | |
| TVOC after 28 days | ISO 16516 | µg/ m3 | <10 |
| Recyclability | - | - | 100% |
| Recycled content | - | - | Up to 30% |
| CE | EN 15 102 | - | OK |

(1) Regarding the resistance to chemicals, please download the corresponding leaflet from our website
(2) The implementation of an effective cleaning regime is the most important defence against infection